

TECHNICAL DATASHEET

ASPOLIT G200

Specific Gravity (g/ml) ISO 787/10-1981	2,75	pH ISO 787/9-1981	9
Mohs Hardness: Mica	2,5	Oil Absorption (g/100 g) ISO 787/5-1980	16
Quartz	7		
Whiteness FMY (%)	70 ± 2	Spec. Surface (m ² /g)	3
Moisture / 100° C (%) ISO 787/2-1981	< 1	Loose Bulk Density (g/l)	740

CHEMICAL ANALYSIS:

SiO ₂	69,0
Al ₂ O ₃	14,0
K ₂ O	5,5
CaO	2,0
Fe ₂ O ₃	2,0
MgO	2,0
TiO ₂	0,4
P ₂ O ₅	0,2
MnO	0,03
Loss on ignition	4,87

HEAVY METALS CONTENT:

µg/g = ppm

Copper	9
Zinc	3,6
Lead	3,9
Cadmium	< 0,2
Mercury	0,03
Arsenic	3

PARTICLE SIZE DISTRIBUTION:

Sedigraph 5100

d98	80 µm
d90	48 µm
d50	18 µm
d30	10 µm

Technical information and data described herein are believed to be reliable, but should not be taken as a specification and cannot establish any liability.